



# Rynite® 940E BK505

## THERMOPLASTIC POLYESTER RESIN

Rynite® 热塑性聚酯的共性包括良好的机械和物理性能，例如强度和刚性之间良好的平衡、尺寸稳定性、耐蠕变、耐热老化、高表面光泽和固有地高温下良好的电气性能。可在很宽泛的温度范围内加工，有很好的流动性能。

Rynite® 热塑性聚酯通常应用于要求严苛的汽车、电子电器工业，成功取代金属、热固性材料和其他热塑性聚合物。

Rynite® 940E BK505是一种40% 玻纤/矿物增强 PET

### 总说明

树脂鉴别	PET-(GF+MD)40	ISO 1043
制品标识码	>PET-(GF+MD)40<	ISO 11469

### 流变性能

模塑收缩率, 平行	0.2 %	ISO 294-4, 2577
模塑收缩率, 垂直	0.7 %	ISO 294-4, 2577

### 机械性能

拉伸模量	12500 MPa	ISO 527-1/-2
断裂应力	110 MPa	ISO 527-1/-2
断裂伸长率	1.8 %	ISO 527-1/-2
弯曲模量	13000 MPa	ISO 178
简支梁无缺口冲击强度, +23°C	35 kJ/m <sup>2</sup>	ISO 179/1eU
简支梁无缺口冲击强度, -40°C	35 kJ/m <sup>2</sup>	ISO 179/1eU
简支梁缺口冲击强度, +23°C	7 kJ/m <sup>2</sup>	ISO 179/1eA
简支梁缺口冲击强度, -40°C	6 kJ/m <sup>2</sup>	ISO 179/1eA
Poisson's ratio	0.33 -	

### 热性能

熔融温度, 10°C/min	250 °C	ISO 11357-1/-3
热变形温度, 1.80 MPa	220 °C	ISO 75-1/-2
热变形温度, 0.45 MPa	241 °C	ISO 75-1/-2
线性热膨胀系数, 平行, -40-23°C	22 E-6/K	ISO 11359-1/-2
线膨胀系数, 平行	15 E-6/K	ISO 11359-1/-2
线性热膨胀系数, 平行, 55-160°C	6 E-6/K	ISO 11359-1/-2
线性热膨胀系数, 垂直, -40-23°C	54 E-6/K	ISO 11359-1/-2
线膨胀系数, 垂直	60 E-6/K	ISO 11359-1/-2
线膨胀系数, 垂直, 55-160°C	84 E-6/K	ISO 11359-1/-2



# Rynite® 940E BK505

## THERMOPLASTIC POLYESTER RESIN

### 燃烧性能

FMVSS Class	B -	ISO 3795 (FMVSS 302)
燃烧速率, 厚度: 1毫米	<80 mm/min	ISO 3795 (FMVSS 302)

### 电性能

相对介电常数., 100Hz	4.2 -	IEC 62631-2-1
相对介电常数., 1MHz	3.9 -	IEC 62631-2-1
介质损耗因子, 100Hz	70 E-4	IEC 62631-2-1
介质损耗因子, 1MHz	146 E-4	IEC 62631-2-1
体积电阻率	1E13 Ohm.m	IEC 62631-3-1
表面电阻率	1E14 Ohm	IEC 62631-3-2
介电强度	33 kV/mm	IEC 60243-1
相对漏电起痕指数	250 -	IEC 60112

### 其它性能

密度	1640 kg/m <sup>3</sup>	ISO 1183
----	------------------------	----------

### 注塑

建议干燥	是
干燥温度	120 °C
干燥时间, 除湿干燥机	4 - 6 h
加工前水分含量	≤ 0.02 <sup>[1]</sup> %
优良熔体温度	285 °C
注塑 熔体温度	280 °C
注塑 熔体温度	300 °C
螺杆大的切线速度	0.2 m/s
优良模具温度	110 °C
模具温度	100 °C
模具温度	120 <sup>[2]</sup> °C
保压范围	≥ 80 MPa
保压时间	4 s/mm
背压	As low as possible MPa
喷射温度	170 °C

[1]: At levels above 0.02%, strength and toughness will decrease, even though parts may not exhibit surface defects.

[2]: (6mm - 1mm thickness)

### 典型数据

添加剂	脱模助剂
-----	------



# Rynite® 940E BK505

## THERMOPLASTIC POLYESTER RESIN

Revised: 2020-04-02

Page: 3 of 3

[dupont.com](http://dupont.com)

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable, and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

**CAUTION:** Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract or other acknowledgement that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.

© 2021 DuPont. All rights reserved.