



POLYPLASTICS CO LTD
18-1 KONAN 2-CHOME
MINATO-KU, TOKYO 108-8280 Japan



Duranex: 330GW

Polybutylene Terephthalate (PBT), pellets, glass reinforced, flame retardant

可燃性	值	测试方法
UL 阻燃等级		UL 94
0.32 mm, NC, BK	V-0	IEC 60695-11-10, -20
0.75 mm, NC, BK	V-0	
1.5 mm, NC, BK	V-0	
3.0 mm, NC, BK	V-0	
灼热丝易燃指数		IEC 60695-2-12
0.32 mm	960 °C	
0.75 mm	960 °C	
1.5 mm	960 °C	
3.0 mm	960 °C	
热灯丝点火温度		IEC 60695-2-13
0.32 mm	960 °C	
0.75 mm	850 °C	
1.5 mm	800 °C	
3.0 mm	960 °C	
电气性能	值	测试方法
热丝引燃 (HWI)		UL 746A
0.32 mm	PLC 3	
0.75 mm	PLC 3	
1.5 mm	PLC 3	
3.0 mm	PLC 0	
高电弧燃烧指数(HAI)		UL 746A
0.32 mm	PLC 0	
0.75 mm	PLC 0	
1.5 mm	PLC 0	
3.0 mm	PLC 0	
相比耐漏电起痕指数(CTI)	PLC 2	UL 746A
漏电起痕指数	325 V	IEC 60112
热性能	值	测试方法
RTI Elec		UL 746B
0.32 mm	140 °C	
0.75 mm	140 °C	
1.5 mm	140 °C	
3.0 mm	140 °C	
RTI Imp		UL 746B
0.32 mm	140 °C	
0.75 mm	140 °C	
1.5 mm	140 °C	
3.0 mm	140 °C	

组件 - 塑料

UL 档案号: E213445



热性能	值	测试方法
RTI		UL 746B
0.32 mm	140 °C	
0.75 mm	140 °C	
1.5 mm	140 °C	
3.0 mm	140 °C	