



POLYPLASTICS CO LTD
18-1 KONAN 2-CHOME
MINATO-KU, TOKYO 108-8280 Japan



Duranex: 522HR
Polybutylene Terephthalate (PBT), pellets

可燃性	值	测试方法
UL 阻燃等级		
0.75 mm, ALL	HB	UL 94
3.0 mm, ALL	HB	UL 94
3.0 mm, ALL	HB40	IEC 60695-11-10, -20
0.75 mm, ALL	HB75	IEC 60695-11-10, -20
电气性能	值	测试方法
热丝引燃 (HWI)		UL 746A
0.75 mm	PLC 3	
3.0 mm	PLC 1	
高电弧燃烧指数(HAI)		UL 746A
0.75 mm	PLC 0	
3.0 mm	PLC 0	
相比耐漏电起痕指数(CTI)	PLC 0	UL 746A
热性能	值	测试方法
RTI Elec		UL 746B
0.75 mm	75.0 °C	
3.0 mm	75.0 °C	
RTI Imp		UL 746B
0.75 mm	75.0 °C	
3.0 mm	75.0 °C	
RTI		UL 746B
0.75 mm	75.0 °C	
3.0 mm	75.0 °C	