



POLYPLASTICS CO LTD
18-1 KONAN
2-CHOME
MINATO-KU, TOKYO 108-8280 Japan



LAPEROS: E481i(h1)

Liquid Crystal Polymer (LCP), pellets

(h1) - Virgin and regrind up to 50% by weight inclusive have the same flammability characteristics with a minimum thickness of 1.5 mm in NC and 0.4 mm in BK.

可燃性	值	测试方法
UL 阻燃等级		UL 94
0.100 mm, NC, BK	V-0	IEC 60695-11-10, -20
0.40 mm, NC, BK	V-0	
1.5 mm, NC, BK	V-0	
3.0 mm, NC, BK	V-0	
热性能	值	测试方法
RTI Elec		UL 746B
0.100 mm	130 °C	
0.40 mm	130 °C	
1.5 mm	130 °C	
3.0 mm	130 °C	
RTI Imp		UL 746B
0.100 mm	130 °C	
0.40 mm	130 °C	
1.5 mm	130 °C	
3.0 mm	130 °C	
RTI		UL 746B
0.100 mm	130 °C	
0.40 mm	130 °C	
1.5 mm	130 °C	
3.0 mm	130 °C	