

# Ultramid® B3WG13 BK00102

## Polyamide 6



### Product Description

Ultramid B3WG13 BK00102 is a 63% glass reinforced, injection molding, high modulus nylon designed to have high strength and stiffness for metal replacement applications. It also has excellent moldability and outstanding surface appearance.

### Applications

Potential applications are mirror brackets, fuel lids, gas-assisted steering wheel inserts, ski bindings and bike rack clamps.

PHYSICAL	ISO Test Method	Property Value	
Density, g/cm <sup>3</sup>	1183	1.74	
MECHANICAL	ISO Test Method	Dry	Conditioned
Tensile Modulus, MPa	527		
23C		22,000	13,400
Tensile stress at break, MPa	527		
23C		235	155
Tensile strain at break, %	527		
23C		2.0	-
Flexural Strength, MPa	178		
23C		355	-
Flexural Modulus, MPa	178		
23C		19,000	-
IMPACT	ISO Test Method	Dry	Conditioned
Izod Notched Impact, kJ/m <sup>2</sup>	180		
23C		15	-
Charpy Notched, kJ/m <sup>2</sup>	179		
-30C		13	-
23C		15	-
Charpy Unnotched, kJ/m <sup>2</sup>	179		
-30C		90	-
23C		90	-
THERMAL	ISO Test Method	Dry	Conditioned
Melting Point, C	3146	220	-
HDT A, C	75	214	-

### Processing Guidelines

#### Material Handling

Max. Water content: 0.12%

Although Product is supplied in sealed containers, drying is recommended in applications requiring optimum surface aesthetics. A dehumidifying or desiccant dryer operating at 80C (176F) is recommended. Drying time is dependent on moisture level, however 2-4 hours is generally sufficient. Recommended water content for molding is 0.08%-0.12%. Further information concerning safe handling procedures can be obtained from the Safety Data Sheet. Alternatively, please contact your BASF representative.

## Typical Profile

Melt Temperature 300-320C (572-608F)  
Mold Temperature 80-95C (176-203F)  
Injection and Packing Pressure 35-125 bar (500-1500 psi)  
Rear Zone 275-300C (527-572F)  
Center Zone 285-310C (545-590F)  
Front Zone 300-320C (572-608F)  
Nozzle 300-320C (572-608F)

## Mold Temperatures

This product can be processed over a wide range of mold temperatures; however, for applications where aesthetics are critical, a mold surface temperature of 80-95C (176-203F) is required.

## Pressures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. Minimal back pressure should be utilized to prevent glass breakage. recommended to minimize glass fiber breakage.

## Fill Rate

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate.

## Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.